

## STOPAQ® EZ TOPCOAT

### Product Information

**Product description:** Stopaq® EZ Topcoat is a water-based, satin gloss, elastomeric top coat based on a modified acrylic elastomer. It has very good UV-resistance and is intended for use as top coat over Stopaq® products with a non-woven top layer like Stopaq® Basecoat LT / Basecoat / Basecoat HT and Stopaq® Wrappingband EZ / EZHT / EZR.

#### Features:

- Single component waterborne top coat
- UV-resistant, suitable as top coat for industrial and marine services
- Very good adhesion to Stopaq® products with non-woven top layer
- Low VOC content, non-flammable

#### Benefits:

- Easy to apply with brush and roller
- Ready to use product

### Application examples

**Atmospheric services:** As topcoat for atmospheric services on Stopaq® Basecoat and Wrappingband products applied on atmospheric pipe structures, structural steel, tank exteriors, roofs, etc.

### Product properties and consumption

<b>Density</b>	1,30 ± 0,05 kg/l [10.8 ± 0.4 lb/gal]
<b>Solids content</b>	59 ± 2 % by mass, 47 ± 2 % by volume
<b>VOC content (EU)</b>	< 60 g/l [0.5 lb/gal]
<b>Flash point</b>	>93 °C [200 °F] (non-flammable)
<b>Gloss</b>	15 ± 5 (Gardner 60°)
<b>Service temperature</b>	Max. 100 °C [212 °F]
<b>Wet film thickness</b>	WFT recommended 200 µm [8 mils] per coat
<b>Number of coats</b>	Minimum 2 layers. Multiple layers may be required for optimum opacity.
<b>Theoretical consumption</b>	Per coat at WFT 200 µm [8 mils]: - 0,20 l/m <sup>2</sup> [0.63 fl. oz. / sq. ft.] - 5,0 m <sup>2</sup> /l [203 sq. ft. / gal.]

### General order information

<b>Product</b>	Stopaq® EZ Topcoat is available in metallic pails of 5 litres [1.32 gal]
<b>Art. Nr.:</b>	<b>Colour:</b>
1090-00500	White
1092-00500	Grey RAL 7032
1093-00500	Grey RAL 7035
1095-00500	Yellow RAL 1023
	Other colours available on request.
<b>Handling</b>	Handle with care. Keep pails upright. See Safety Data Sheet for further details.
<b>Storage</b>	Store indoor, clean and dry, away from direct sunlight in a well-ventilated and cool place between +5 and 35 °C [41 to 95 °F]. Keep from freezing. See Safety Data Sheet for further details. Shelf life 24 months.

### Application instruction – Job preparation

<b>OHSE measures</b>	See Safety Data Sheet for appropriate personal safety measures, personal protective gear, application conditions, etc.
<b>Tools, equipment and auxiliaries</b>	Brushes: flat longhaired nylon or polyester Rollers: nylon or polyester
<b>Work area and substrate</b>	The substrate must be dry, clean and protected against negative weather influences.
<b>Product conditions</b>	Stopaq® EZ Topcoat must be uniform in consistency which can be obtained by proper mixing. The temperature must be not less than 5 °C [41 °F] and should preferably be 12 to 25 °C [54 to 77 °F]

### Application instruction – Surface preparation

<b>General</b>	The area to be coated must be clean, dry, and free from oil, grease and dust. All contamination that can interfere with adhesion of Stopaq® EZ Topcoat must be removed.
<b>Ambient, humidity and dew point</b>	Ambient and substrate temperature ≥ 5 °C [41 °F] Relative humidity ≤ 80 % Substrate temperature ≥ 3 °C [5 °F] above dew point

### Application instruction – Brief version

See specific instructions for application on objects coated with products like Stopaq® Basecoat or Stopaq® Wrappingband EZ/EZR.	
<b>Application</b>	Apply Stopaq® EZ Topcoat in recommended wet film thickness. The recommended number of coats can be applied wet-on-wet.
<b>Visual inspection</b>	The applied layers of Stopaq® EZ Topcoat should be free from voids, sags and striations.
<b>Drying times</b>	At 20 °C [68 °F] and 50 % RH: - Dry to touch: 2 hours - Dry to recoat: 4 hours

### Handling and commissioning

<b>Exposure to loads</b>	Objects coated with Stopaq® EZ Topcoat should not be exposed to loads e.g. from supports or lifting equipment.
<b>Commissioning</b>	Commissioning is possible after recoat time has been reached. Consult data sheets for specific instructions of additional coating materials used.

### Information

<b>Documentation</b>	Extensive information is available on our website. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending an email to <a href="mailto:info@sealforlife.com">info@sealforlife.com</a>
<b>Certified staff</b>	Application of the described coating system should be carried out by certified personnel.